

INDUSTRIAL COATING SPECIALTIES CORPORATION

PAINTS-EPOXIES-INDUSTRIAL FINISHES

5521 MITCHELLEDALE- (713) 686-3411

HOUSTON, TEXAS 77092

FAX (713) 686-8725

THERMO-ADHESIVE

GENERIC TYPE	Methylmethacrylate copolymer
PIGMENTATION	None
SOLIDS	20% by weight
THEORETICAL COVERAGE	300 sq. ft./gal
NORMAL COVERAGE	250 sq. ft./gal.
SURFACE PREPARATION	Clean; free of oil
REDUCER	ICSC #30 Thinner
DRY TIME	15 minutes @77°F
RECOAT TIME	1 hour
CURING AGENT	N/A
MIX RATIO	N/A
POT LIFE	N/A
APPLICATION	Conventional or airless spray
CLEAN UP	ICSC #30 Thinner
COMMENTS	Intercoat primer for thermoplastic striping.