

TEST REPORT

Applicant :

Date : Nov 17, 2020

DISTRICT ,ZHENJIANG CITY
JIANGSU,CHINA

Attn :

Sample Description As Declared :

No. Of Samples : Twenty (20)
Fibre Content : Nitrile
Sample Name : (A) SWALLOW-JIALI-S (B) SWALLOW-JIALI-M (C) SWALLOW-JIALI-L (D) SWALLOW-JIALI-XL
Finishing : -
End Uses : Hand Protection
Colour : Blue
Style No. : SWALLOW-JIALI-S / SWALLOW-JIALI-M / SWALLOW-JIALI-L / SWALLOW-JIALI-XL
Order No./PO No. : GPPE/201102/01
Buyer's Name : GLOBAL PPE
Manufacturer's Name : ZHANJIANG JIALI GLOVE PRODUCTS CO., LTD
Agent Name :
Standard : -
Ref. : Fabric/Garment Weight: 4.5-6G

Applicant's Provided Care Instruction/Label : -

Date Sample Received : Nov 17, 2020

Date Testing Started : Nov 17, 2020

Prepared And Checked By:
For Intertek Testing Services Ltd.,Shanghai



Jennifer Ren
General Manager

TEST REPORT

Tests Conducted (As Requested By The Applicant)

2 Thickness (ASTM D1777-96(2015), Modify, Measured Under A Pressure Of 3.4 lbs/in² After 5 seconds):

<u>Double Thickness</u>	(A1)	(A2)	(A3)
Finger	0.19 mm	0.19 mm	0.18 mm
Palm	0.16 mm	0.15 mm	0.16 mm
Cuff	0.12 mm	0.12 mm	0.13 mm

<u>Double Thickness</u>	(A4)	(A5)
Finger	0.19 mm	0.20 mm
Palm	0.17 mm	0.15 mm
Cuff	0.13 mm	0.14 mm

<u>Double Thickness</u>	(B1)	(B2)	(B3)
Finger	0.19 mm	0.18 mm	0.19 mm
Palm	0.17 mm	0.147 mm	0.15 mm
Cuff	0.13 mm	0.14 mm	0.13 mm

<u>Double Thickness</u>	(B4)	(B5)
Finger	0.18 mm	0.19 mm
Palm	0.17 mm	0.15 mm
Cuff	0.12 mm	0.13 mm

<u>Double Thickness</u>	(C1)	(C2)	(C3)
Finger	0.19 mm	0.19 mm	0.17 mm
Palm	0.16 mm	0.15 mm	0.14 mm
Cuff	0.13 mm	0.13 mm	0.11 mm

<u>Double Thickness</u>	(C4)	(C5)
Finger	0.17 mm	0.19 mm
Palm	0.15 mm	0.17 mm
Cuff	0.13 mm	0.12 mm

<u>Double Thickness</u>	(D1)	(D2)	(D3)
Finger	0.18 mm	0.20 mm	0.19 mm
Palm	0.14 mm	0.15 mm	0.14 mm
Cuff	0.102 mm	0.13 mm	0.12 mm

<u>Double Thickness</u>	(D4)	(D5)
Finger	0.19 mm	0.18 mm
Palm	0.15 mm	0.163 mm
Cuff	0.13 mm	0.12 mm

TEST REPORT

Tests Conducted (As Requested By The Applicant)

3 Product Weight:

(A1) 4.7 g/piece (0.1 lbs/doz)	(A2) 4.8 g/piece (0.1 lbs/doz)	(A3) 4.8 g/piece (0.1 lbs/doz)	(A4) 4.7 g/piece (0.1 lbs/doz)	(A5) 4.6 g/piece (0.1 lbs/doz)
(B1) 5.0 g/piece (0.1 lbs/doz)	(B2) 5.1 g/piece (0.1 lbs/doz)	(B3) 5.0 g/piece (0.1 lbs/doz)	(B4) 5.0 g/piece (0.1 lbs/doz)	(B5) 5.1 g/piece (0.1 lbs/doz)
(C1) 5.5 g/piece (0.1 lbs/doz)	(C2) 5.6 g/piece (0.1 lbs/doz)	(C3) 5.4 g/piece (0.1 lbs/doz)	(C4) 5.5 g/piece (0.1 lbs/doz)	(C5) 5.4 g/piece (0.1 lbs/doz)
(D1) 5.8 g/piece (0.1 lbs/doz)	(D2) 5.9 g/piece (0.1 lbs/doz)	(D3) 5.9 g/piece (0.1 lbs/doz)	(D4) 6.0 g/piece (0.1 lbs/doz)	(D5) 5.8 g/piece (0.1 lbs/doz)

End of Report

Remark: This statement of conformity is only based on the actual measured test result by the laboratory, without taking the influence of uncertainty into account.

This report is made solely on the basis of your instructions and/or information and materials supplied by you. It is not intended to be a recommendation for any particular course of action. Intertek does not accept a duty of care or any other responsibility to any person other than the Client in respect of this report and only accepts liability to the Client insofar as is expressly contained in the terms and conditions governing Intertek's provision of services to you. Intertek makes no warranties or representations either express or implied with respect to this report save as provided for in those terms and conditions. We have aimed to conduct the Review on a diligent and careful basis and we do not accept any liability to you for any loss arising out of or in connection with this report, in contract, tort, by statute or otherwise, except in the event of our gross negligence or wilful misconduct.

This report shall not be reproduced except in full, without written approval of the laboratory.