

// LEGION PRO™ 2.0



TEST	UNIT	SPECIFICATIONS
Linear Density - Denier Mono*	Denier	10,800
Linear Density - Denier Tape*	Denier	5,000
Thickness - Mono**	Microns	300
Thickness - Tape**	Microns	100
Break Strength - Mono***	lbs/force	20
Break Strength - Tape***	lbs/force	12
Elongation - Mono & Tape	%	> 30
Total Lead Content - Mono & Tape	ppm	< 100
Total Product Weight****	oz / yd ²	74
Pile Yarn Fiber Weight**	oz / yd ²	46
Primary Backing Weight**	oz / yd ²	8
Secondary Backing Weight†	oz / yd ²	20
Average Pile Height**	inches	2.0
Average Tuft Bind Strength	lb / force	> 10
Tufting Gauge	inches	1/2
Average Grab Tear Strength	lb / force	> 200
g-Max		< 200
Pill Flammability		Pass
Infiltrometer (Drainage)	in / hr	> 25

Except where noted as a minimum or maximum, the above specifications are nominal.

* All values are ± 8% ** All values are ± 5% *** All values are ± 25% **** All values are ± 10% † All values are ± 3 oz



The colors shown are not intended for exact matching purposes, please refer to actual sample swatches for accurate hues.